OMNISPORTS Active +, Pureplay, Reference Multi-Use, Installation instructions





PREFACE

In order to provide the customer with the best use of product, this installation guide has to be followed carefully to guarantee conformity and ensure sports performance. If not, Tarkett Sports will not be responsible for damages following installation.

Any use of the product for purposes other than the ones set out, in the condition of use, should be submitted to Tarkett Sports for prior approval. If you need any further information, please contact your dealer who will provide you with the appropriate advice.



Check before installation, the quality of the delivered product, rolls must be received on site in a protective cardboard. If the product is defective, contact Tarkett Sports. If installation is in process, it shall be stopped on the day the defect is noticed otherwise the Warranty shall not apply.



SUBFLOOR

The subfloor must be dry, flat, clean, strong and without cracks.

The moisture rate for concrete or cement screed must be in accordance with the local requirements.

For example : France ≤ 4,5% and Germany < 2% (CCM method),...

Choice of laying techniques Subfloor	Glued	Tarkolay	GreenLay
Surface appearance	Smooth		
Flatness	≤ 6mm under 3m ruler		
Altimetry	+/- 1cm compared to the average		
Moister rates for concrete	Local standard compliant	≤ 7%	≤ 7%
Moister rates for anhydrite screed	< 0,5%	< 1%	< 0,5%
Saw joints treatment	Yes	Yes	Yes
Cracks < 1mm treatment	Yes	No	Yes
Levelling compound (necessary if the surface appearance is not smooth or if the flatness is not compliant)	If the concrete is exposed to capillary moisture surges, it's necessary to waterproof the subfloor by an epoxy resin (or equivalent) before applying the levelling compound	For localized concrete repair, use a specific moisture-resistant levelling.	For localized concrete repair, use a specific moisture-resistant levelling.

Important notice: no expansion joints shall be present in the playing area



1 - GENERAL CONDITIONS



The temperature in the room must be \geq 15°C and for the subfloor \geq 12°C. Relative air rate moister needs to be between 35 et 65%.

Omnisports rolls are to be stored horizontally, on a plain/flat, dry and without any ruggedness. They must not be stacked.





Tarkett Sports recommend to install rolls in the play direction. For a glued installation, Omnisports can be installed in the transversal direction. Same batch for all the same room.

Mark out transversal and longitudinal axes.


Unroll the rolls along the longitudinal axis, following the chronological rolls manufacture order, leaving a space of 1 cm between them for at least 24 hours.

If necessary, re-cut the selvedge

Let the Omnisports rest before adjusting the sheets, edge-to-edge, gap < 1mm.

Uni: alternate direction

Wood patterns: same way





2 - GREENLAY INSTALLATION



GreenLay installation is not allowed in gymnasiums with large roof windows. After installation, ensure that the temperature is always maintained between 10 and 38°C.


Sheets are fixed on the subfloor (except for the central joint of the gymnasium) by using double sided adhesive tape – Tarkotape (double sided tape) ref 1551185 (1 roll = 152mm width x 25lm, sold in 1 box of 8 rolls = 200lm).

If the subfloor is too absorbent, apply a primer to the subfloor on the right side of the double-sided tape and glue.

The gluing areas with bi-component GreenLay Glue (Component A reference 1551057. Component B reference 1551058) and a thin toothed spatula TKB A2 (300 to 350gr per sqm) should be handled as follows:


- Central join (transversal axis), 25cm on each side,
- External edges (at periphery of the gymnasium), 100cm² every meter,
- All around the trap doors edges, 20cm width,
- In front of all the doors, 20cm width.

Then, press the surface with a roller to eliminate any bubbles that might remain between the sub-floor and the covering.





If you install two or three coloured projects, you will have to glue the seams under the different colours with GreenLay Glue.



NOTA: If there are telescopic bleachers on Omnisports, Tarkett Sports recommends to glue the floorcovering in the dedicated area (Cf. Glued installation). Please check appropriate reinforcement solutions in our Maintenance guide.

3 - GLUED INSTALLATION



After installation, ensure that the temperature is always maintained between 10 and 45°C.

Roll half way back the sheets carefully on the first half of the gymnasium and start from the longitudinal axis to avoid moving the sheets from their original positions.

Apply the acrylic glue on the uncovered half of the sub-floor, starting with the center strips and working outwards.

Only glue the adequate surface of floor covering, considering the drying time in order to make the glue transfer effective to floor covering back (maximum two or three sheets at the same time).

For a normal absorbent sub-floor, glue consumption is about 250-300gr/sqm with a thin toothed spatula TKB A2.

Lay Omnisports rolls on the sub-floor and make sure that setting time specified by the glue manufacturer is respected. Start by the first one along the longitudinal axis.

Press all the surface glued with cork to eliminate the air bubbles located between the subfloor and Omnisports then use a 50kg heavy roller, this will enable the glue to transfer perfectly on Omnisports.

Repeat the same operations for the second half Omnisports sheets and the second half of the gymnasium.

Don't leave any heavy load on Omnisports during the whole glue drying time (72h).



3 - INSTALLATION OVER TARKOLAY



After installation, ensure that the temperature is always maintained between 10 and 45°C.

Tarkolay installation:


Unroll Tarkolay in the same direction as the Omnisports, with studs on subfloor side, and align the strips edge to edge.

If you might have to cut a roll and join it with another one, do not forget to tape the short ends of the two sheets together on their backside, using a single sided tape.

Leave 5mm ventilation gap all around the periphery of the gymnasium.

The gluing areas with bi-component GreenLay Glue (Component A reference 1551057. Component B reference 1551058) and with a thin toothed spatula TKB A2 (300 to 350gr per sqm) should be handled as follows:

- External edges (at periphery of the gymnasium), 100cm² every meter,
- All around trap doors edges, 20cm width,
- In front of all the doors, 20cm width.





Installation instructions

INSTALLATION

Omnisports installation over Tarkolay:

Mark out tranversal and longitudinal axis on Tarkolay.

Position Tarkolay selvedges 50cm from Omnisports ones.

Unroll Omnisports along the longitudinal axis, following rolls manufacture chronological order, leaving a space of 1 cm between them for at least 24 hours and if necessary, re-cut the selvedge.

Let Omnisports rolls rest before adjusting the sheets, edge-to-edge, space < 1mm.

Roll half way back the sheets carefully on the first half of the gymnasium and start from the longitudinal axis to avoid moving the sheets from their original positions.

Omnisports should be glued with our polyurethane adhesive Greenlay Glue.

Glue consumption is about 300-350gr/sqm with a thin toothed spatula (TKB A5).

Apply the glue on sub-floor uncovered half, starting with the center strips and working outwards.

Only glue the adequate surface of Omnisports, there is no waiting time.

Start to lay down Omnisports rolls by the first one along the longitudinal axis.

Press all the surface glued with cork to eliminate the air bubbles located between the subfloor and the foam backing then use a 50kg heavy roller, this will enable the glue to transfer perfectly on the floor covering.

Repeat the same operations for the second half sheets and the second half of the gymnasium.

Don't walk on floorcovering until next day.

Don't leave any heavy load on the floor covering during the complete glue drying time (72h).





Installation instructions

INSTALLATION

5 - HOT WELDING




24 hours after gluing, immediately on Tarkotape

The grooving:

This operation should be performed by using an electric tool with a "U" shaped blade as described, for any 5mm diameter welding rod the width of mill must be 4.3mm and maximum depth 2.5mm.





The welding:

We strongly recommend, for this operation, an automatic cart (Leister or similar), which will produce more regular, professional quality welds.


Before welding Omnisports, first of all, try to weld on an apart piece of product, in order to check that the temperature and the speed of this material enables to perform a good welding conditions.

To obtain an optimal result, we recommend to set the temperature on 450°C, speed: 2m/min.







The trimming:



The presence of a small bump indicates the perfect level of fusion of the welding rod.



First trim with a Mozart knife and wedge before cooling.



Second trim with a Mozard knife after cooling.







5 - PAINTING GAME LINES

1 Permanent marking:

- Blanchon Thixo Tracé Blanchon SA Tel: +33 4 72 89 06 00 www.blanchon.com
- Kipp 2K PUR Indoor for lines marking and Kipp 2K PUR Surface Paint for the surfaces
 Tél +49 7154 82420 www.kipp-markierungen.de
- Bona SuperSport Line Paint Bona Tel: +4640385500 E-mail: bona@bona.com www.bona.com
- Conipur 3100 BASF AG- Tél. +41 58 958 22 44 -www.conica.com

Follow the manufacturer's installation recommendations.

2 Temporary marking lines:

The producer of these tapes is 3M - reference 471 - 5cm width -www.3M.com



ANH NGOC THANH TRADING COMPANY LIMITED (ANTRADE CO., LTD.)

HCM office: R. 5.03, 5th Fl., Phuong Tower, 31C Ly Tu Trong Str., Ben Nghe W., Dist.1, HCMC. Tel: (+84) 28 38257622 / 28 38257623

Website: www.antrade.vn

Hotline: +84 933 662138

Tel: (+84) 24 63289487 / 24 39749263 62138 Email: sales@antrade.vn

HN office: R.701, 7th Fl., 131 Bui Thi Xuan Str.,

Hai Ba Trung District, Ha Noi City, Vietnam.