



Installation Method



Ashlar

Herringbone

All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see www.interface.com/disclaimer.

Product Works Eon **Colour** Ebony **Collection** Work Series Collection **Backing** GlasBac™

Product Specifications

Product Construction	Tufted Textured Loop
Yarn System	100% Solution Dyed Nylon
Yarn Manufacturer	Universal
Dye Method	100% Solution Dyed

More Product Specifications

	Imperial	Metric
Tufted Pile Weight	12.00 oz/yd ²	407.00 g/m ² ± 5%
Machine Gauge	1/12 in	47.2 ends/10cm
Stitches	13.20 in	52.00 ends/10cm
Pile Thickness	0.08 in	2.00 ±0.5 mm
Total Thickness	0.197 in	5 mm ±0.5 mm
Size Description	9.84 in x 39.37 in	25cm x 1m

Performance Specifications

Area of Use	Commercial - General Use
Stability - Delaminating	ASTM D3936 ≥ 2.5lbs/in AS/NZS 2111.16 ≥ 50 Newtons
Stability - Dimensional Stability	ISO 2551 ≤ 0.2% ISO/PAS 17984 < 0.2%
Stability - Tuft Bind	AS/NZS 2111.15 >30 Newtons
Wear - Castor Chair	BS-EN 985 r ≥ 2.4
Wear - Vetterman Drum	TWC-TM247 / TWC-TM251 / TWC-TM284 Colour: ≥3 & Structure: ≥3 BS ISO 10361 Overall Change ≥3.5
Colour Fastness to Light	AATCC 16E ≥ 4 AS2001 1.4.21 ≥ 4
Colour Fastness to Rubbing and Crocking	AATCC 165 ≥ 4 AS/NZS2111.19.1 ≥ 4
Colour Fastness to Water	AATCC 107 ≥ 4 AS2001.4.21 ≥ 4
Flammability - Methanamide Pill	BS6307/ISO 6925 Radius ≤ 7.6
Flammability - Radiant Panel	ASTM E648 Class 1 ISO 9239-1 B1
Flammability - Smoke density	ISO 9239-1 Density < 750 %min ASTM E662 Density ≤ 450
Antistatic	AATCC 134 < 3000 Volts
Antimicrobial Treatment	AATCC 171 Washed AATCC174 Parts 2 & 3 99% reduction. No mold 7 Days ASTME-2471 Complete Inhibition

Generic Tests

Acoustic - Nylon	Absorption Coefficient - NRC ≥ 0.10
Dynamic Loading	AS/NZS 2111.2 < 12.5% loss ISO 2094 ≥ 85%
Green Carpet (VOC)	ASTM D5116 Accredited ISO 10580 Accredited
Static Loading	AS/NZS2111.13 < 6% Loss ISO 015/3415 Thickness after 60 mins recovery >85%
Thermal Resistance	ASTM C518 R Value ≥ 0.5

Environmental Specifications

Recycled Content %	48 %
Pre-Consumer (Total)	46.00 %
Post-Consumer (Total)	1.00 %
Ingredients and Life Cycle Impacts	View Our Environmental Product Declarations
Other Environmental Claims	View Environmental Accreditations
End of Life	Carpet to Carpet Recycling
Embodied Carbon (Cradle to Gate)	4.9 kg CO ₂ eq./m ²
Full Life Cycle Carbon	Certified Carbon Neutral Floors™

Technical Information

Installation	View recommended Interface Installation Guidelines online
Maintenance	View recommended Interface Maintenance guidelines online
Reclamation	View details on our ReEntry™ Program

Warranty 15 Year Standard Warranty

Manufacturing Location ISO9001&14001&45001 Certified Plant in Taicang, China
