



Installation Methods



Ashlar Herringbone

All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see www.interface.com/disclaimer

Collection Works Series **Product** Works Unite **Colour** 2396-001-000 Sage

Product Specifications

Product Number	2396
Product Construction	Tufted Loop Pile
Yarn / Fibre	BCF Nylon Type 6
Yarn Manufacturer	Universal
Colour System	100% Solution Dyed
Soil/Stain Protection	Protekt ^{2®}
Preservative Protection	Intersept [®]
Tufted Pile Weight	14 oz/yd ² ±10% 475 g/m ² ±10%
Machine Gauge	12th Gauge
Stitches	41/10cm 10/in
Pile Thickness	2.5 mm ± 0.5mm
Total Thickness	5.5 mm ± 0.5mm
Size Description	25cm X 1m
Backing Structure (Learn more)	GlasBac [®]

Performance Specifications

Area of Use	Commercial - General Duty
ACCS	Commercial Extra Heavy Duty & Stairs
Stability - Delaminating	ASTM D3936 ≥ 2.5lbs/in AS/NZS 2111.16 ≥ 50 Newtons
Stability - Dimensional Stability	ISO 2551 ≤ 0.2% ISO/PAS 17984 < 0.2%
Stability - Tuft Bind	AS/NZS 2111.15 >30 Newtons ASTM D1335 ≥ 8.0lbs
Wear - Castor Chair	BS-EN 985 r ≥ 2.4
Wear - Vetterman Drum	TWC-TM247 / TWC-TM251 / TWC-TM284 Colour: ≥3 & Structure: ≥3,BS ISO 10361 Overall Change ≥3.5
Colour Fastness to Light	AS2001 1.4.21 ≥ 4 AATCC 16E ≥ 4
Colour Fastness to Rubbing and Crocking	AATCC 165 ≥ 4 AS/NZS2111.19.1 ≥ 4
Colour Fastness to Water	AATCC 107 ≥ 4 AS2001.4.21 ≥ 4
Flammability - Methanamine Pill	BS6307/ISO 6925 Radius ≤ 7.6
Flammability - Radiant Panel	ASTM E648 Class 1 ISO 9239-1 B1
Flammability - Smoke density	ASTM E662 Density ≤ 450 ISO 9239-1 Density < 750 %.min
Antistatic	AATCC 134 < 3000 Volts BS ISO 6356 ≤ 2.0Kv
Antimicrobial Treatment	ASTME-2471 Complete Inhibition AATCC 171 Washed AATCC174 Parts 2 & 3 99% reduction. No mold 7 Days

Generic Tests	
Acoustic - Nylon	Absorption Coefficient - NRC \geq 0.10
Dynamic Loading	AS/NZS 2111.2 < 12.5% loss
Green Carpet (VOC)	ASTM D5116 Accredited
Static Loading	AS/NZS2111.13 < 6% Loss
	ISO 015/3415 Thickness after 60 mins recovery >85%
Thermal Resistance	ASTM C518 R Value \geq 0.5
Environmental Specifications	
Recycled Content %	45-57
Other Environmental Claims	View Environmental Accreditations
Ingredients and Life Cycle Impacts	View our Environmental Product Declarations
End of Life	Carpet to Carpet Recycling
Carbon Neutral Floors™	Standard
Technical Information	
Maintenance	View recommended Interface Maintenance guidelines online
Reclamation	View details on our ReEntry™ Program
Warranty	15 Year Standard Warranty
